

Data sheet

GRADE
ZZC 500

ARBOCEL[®]

natural cellulose fibres

Basic raw material

technical raw cellulose

Characteristic

medium sized fibre, grey

Physical and chemical properties

cellulose content	approx. 80 %
average fibre length	400 µm
average fibre thickness	45 µm
bulk density	75 g/l - 105 g/l
residue on ignition (850 °C, 4 h)	approx. 15 %
pH-value	7,5 +/- 1

Screen analysis

Screen residue (in accordance with DIN 53 734/air jet sieve) with an interior mesh aperture of:

<u>200 µm</u>	<u>32 µm</u>
max. 10 %	max. 90 %

As with all natural products slight differences to the above given values may arise.

General references

ARBOCEL[®] cellulose fibres are environment friendly products, gained from replenishable raw materials.

Among other things, they are used as thickeners, for fibre reinforcement, as an absorbent and diluent or as a carrier and filler in most manifold application fields.



J. RETTENMAIER & SÖHNE GMBH + CO
Manufacturers of Fibres
Holzmühle 1
D-73494 Rosenberg

Telephone: 0 79 67/1 52-0
Telefax: 0 79 67/ 1 52 - 222

9609