

# Bermocoll EBM 3000

Bermocoll® EBM 3000 is a non-ionic, water soluble cellulose ether with enhanced enzyme resistance. It improves the consistency, the stability, and the water retention of water based products.

## Specifications

Appearance	White powder
Particle size	98 % ≤ 500 µm
Salt content	≤6 %
Water content	≤4 %

## Characteristics

pH, 1% solution	5-7
Surface activity	Weak
Viscosity at 20 °C (Brookfield LV), 1% solution	2000-3000 mPa.s

### Notes:

Bermocoll® EBM 3000 is a medium viscosity grade of methyl ethyl hydroxyethyl cellulose

## Applications

Bermocoll® EBM 3000 is used in latex paints for thickening and stabilizing effects, particularly when high storage viscosity combined with low application viscosity is required. Normal dosage is 0.2 - 0.7 % calculated on the total paint weight. Bermocoll® EBM 3000 is easily dispersed in cold water of pH 7 or less. Bermocoll® EBM 3000 can form lumps when added to an alkaline liquid. To avoid this, it should be added as a ready stock solution, as a slurry in slight acid water or in an organic solvent, or as a dry mix with other powder materials. The dissolving time after dispersion is influenced by the water pH. Alkaline additives can be used to speed up the dissolving process.

## Storage

In unopened bags, Bermocoll® EBM 3000 can be stored for several years. In opened bags, the moisture content of Bermocoll® EBM 3000 will be influenced by the air humidity. At the temperatures above 250 °C (480 °F), charring of Bermocoll® EBM 3000 will occur.

## Packaging and transport

Bermocoll® EBM 3000 is packed in a polyethylene bag. Net weight 20 kg. We recommend emptying the bags from the bottom. The empty bags can be recycled or burned.

## Safety and handling

Dust formation can cause explosions and must be avoided or kept to a minimum. Care should be taken to prevent ignition from heat, spark, open flames or hot surface. At high temperatures and in contact with an open flame, Bermocoll® EBM 3000 will burn slowly with the characteristics of cellulose.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

For more information, please visit our website at [www.nouryon.com](http://www.nouryon.com).

